Toughblend® PP-1400

Polypropylene

Colour Image Plastic Compound Sdn. Bhd. (CIPC)

Message:

Toughblend ® PP-1400 is a glass fiber reinforced coupled polypropylene compound. It's offering high rigidity and higj heat deflection temperatures and high impact strength.

General Information					
Filler / Reinforcement	Glass Fiber,20% Filler by Weight				
Features	Chemically Coupled				
	Good Impact Resistance				
	High Heat Resistance				
	High Rigidity				
Uses	Automotive Applications				
	Industrial Parts				
Forms	Pellets				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.04	g/cm³	ASTM D792		
Molding Shrinkage - Flow (3.20 mm)	0.20 to 0.50	%	ASTM D955		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength	71.0	MPa	ASTM D638		
Tensile Elongation (Break)	3.5	%	ASTM D638		
Flexural Modulus	3600	MPa	ASTM D790		
Flexural Strength	105	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (23°C)	97	J/m	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		
Deflection Temperature Under Load			ASTM D648		
0.45 MPa, Unannealed, 4.00 mm	162	°C			
1.8 MPa, Unannealed, 4.00 mm	130	°C			
Flammability	Nominal Value		Test Method		
Flame Rating (1.60 mm)	НВ		UL 94		
Injection	Nominal Value	Unit			
Drying Temperature	100	°C			
Drying Time	2.0 to 4.0	hr			
Rear Temperature	190 to 200	°C			
Middle Temperature	200 to 210	°C			

Front Temperature	210 to 220	°C	
Nozzle Temperature	220 to 230	°C	
Processing (Melt) Temp	190 to 230	°C	
Mold Temperature	60.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

