

STYRON™ 487

High Impact Polystyrene

Americas Styrenics LLC

Message:

STYRON™487 is a high impact polystyrene material. This product is available in North America and is processed by extrusion or injection molding.

STYRON™The main features of the 487 are:

- flame retardant/rated flame
- accessible food
- Good toughness
- Heat resistance

Typical application areas include:

- packing
- electrical appliances
- home apps
- hat/cap/cork
- food contact applications

General Information	
UL YellowCard	E326906-100171512
Features	Good fine tuning
	Heat resistance, high
	Good toughness
	Compliance of Food Exposure
Uses	Packaging
	Electrical appliances
	Cover
	Household goods
Agency Ratings	FDA 21 CFR 177.1640
UL File Number	E326906
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	2.8	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 - 0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	106		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	2000	MPa	ASTM D638
Tensile Strength			ASTM D638

Fracture, injection molding	28.0	MPa	ASTM D638
Injection Molding	31.0	MPa	ASTM D638
Tensile Elongation (Break, Injection Molded)	85	%	ASTM D638
Flexural Modulus (Injection Molded)	2280	MPa	ASTM D790
Flexural Strength (Injection Molded)	34.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
23°C, molded	110	J/m	ASTM D256
23°C, injection molding	140	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	92.0	°C	ASTM D648
1.8 MPa, not annealed	81.0	°C	ASTM D648
Vicat Softening Temperature	104	°C	ASTM D1525
CLTE - Flow	9.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	218 - 249	°C	
Middle Temperature	218 - 249	°C	
Front Temperature	199 - 213	°C	
Nozzle Temperature	213 - 243	°C	
Mold Temperature	15.6 - 65.6	°C	
Injection Rate	Fast		
Back Pressure	0.200 - 1.20	MPa	
Cushion	6.35	mm	
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	177 - 193	°C	
Cylinder Zone 2 Temp.	182 - 204	°C	
Cylinder Zone 3 Temp.	188 - 210	°C	
Cylinder Zone 4 Temp.	199 - 216	°C	
Cylinder Zone 5 Temp.	204 - 221	°C	
Adapter Temperature	193 - 232	°C	
Melt Temperature	193 - 232	°C	
Die Temperature	199 - 232	°C	
Extrusion instructions			

Zone 6 Temperature: 204 to 221°C Melt Pump, Pipes, Screen Changer Temperature: 193 to 232°C Polish Rolls Temperature: 66 to 104°C Head Pressure: 10 to 21 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

