

Baoding 6126H

Thermoplastic Polyurethane Elastomer

Baoding Bangtai Polymeric New-Materials Co.,Ltd

Message:

Properties: Hot melt adhsvie film. It can also used with MEK and EAC when dissolved. Also with high crystallization rate and especially has great bonding capacity with TPU, PVC, NYLON, and fabric.

Applications: Application: Fire hose, Shoe, Water seal, Ink print, Anti-explosion glass used into the high buildings.

| General Information | | |
|---------------------------------|--------------------------|-------|
| Features | Bondability | |
| | Good Adhesion | |
| Uses | Adhesives | |
| | Footwear | |
| | Hose | |
| | Printing Ink | |
| | Seals | |
| Appearance | White | |
| Physical | Nominal Value | Unit |
| Solution Viscosity ¹ | 3600 to 4200 | mPa·s |
| Thermal | Nominal Value | Unit |
| Vicat Softening Temperature | 55.0 to 65.0 | °C |
| Additional Information | Nominal Value | Unit |
| Flow Beginning Temperature | 90 to 100 | °C |
| NOTE | | |
| 1. | 15% solid content in MEK | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT