

POCAN® B 3215 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, 10 % glass fibers, injection molding

General Information			
UL YellowCard	E245249-100586882		
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Processing Method	Injection Molding		
Multi-Point Data	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
	1.38		
Density (23°C)	1.38	g/cm ³	ISO 1183
Apparent Density	0.70	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	30.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow : 260°C, 2.00 mm ¹	1.1	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.10	%	
Flow : 260°C, 2.00 mm ³	0.90	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	%	
Water Absorption			ISO 62
	0.40		
Saturation, 23°C	0.40	%	
	0.20		
Equilibrium, 23°C, 50% RH	0.20	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	150	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
23°C	4750	MPa	ASTM D638
23°C	4900	MPa	ISO 527-2/1

Tensile Strength			
Break, 23°C	95.1	MPa	ASTM D638
Break, 23°C	90.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	4.0	%	ISO 527-2/5
Flexural Modulus			
23°C	3990	MPa	ASTM D790
23°C ⁵	4600	MPa	ISO 178/A
Flexural Strength			
23°C	138	MPa	ASTM D790
3.5% Strain, 23°C	135	MPa	ISO 178/A
23°C ⁶	145	MPa	ISO 178/A
Flexural Strain at Flexural Strength (23°C) ⁷	5.1	%	ISO 178/A
Halving Interval			IEC 60216
Electric Strength	11.4	°C	
Tensile Impact Strength	9.3	°C	
Tensile Strength	14.0	°C	
Temperature Index			IEC 60216
Electric Strength, 20000 hr	160	°C	
Tensile Impact Strength, 20000 hr	140	°C	
Tensile Strength, 20000 hr	150	°C	
Electrolytical Corrosion (23°C)	A 1		IEC 60426
ISO Shortname	PBT, GHMR, 09-050, GF10		ISO 7792
	0.0 to 0.020		
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	25	kJ/m ²	
23°C	25	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-40°C	< 10	kJ/m ²	
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	20	kJ/m ²	
23°C	20	kJ/m ²	
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-30°C	1.50	J	

23°C	1.50	J	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	190	°C	ISO 75-2/A
Vicat Softening Temperature	205	°C	ISO 306/B120
Ball Pressure Test (212°C)	Pass		IEC 60695-10-2
Melting Temperature ⁸	222	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	5.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	1.3E-4	cm/cm/°C	
RTI Elec	140	°C	UL 746
RTI Imp	125	°C	UL 746
RTI Str	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity (23°C)	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	30	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.60		
23°C, 1 MHz	3.40		
Dissipation Factor			IEC 60250
23°C, 100 Hz	1.5E-3		
23°C, 1 MHz	0.018		
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
Glow Wire Flammability Index (2.00 mm)	750	°C	IEC 60695-2-12
Oxygen Index ⁹	20	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
	4.0 to 8.0		
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		

3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min
9.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

