# RTP 400 SI 1

## General Purpose Polystyrene RTP Company

### Message:

Warning: The status of this material is 'Commercial: Limited Issue' The data for this material has not been recently verified.

Please contact RTP Company for current information prior to specifying this grade.

General Information			
Additive	Silicone Lubricant (1%)		
Features	Lubricated		
RoHS Compliance	Contact Manufacturer		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.040	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3450	MPa	ASTM D638
Tensile Strength	41.4	МРа	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	3450	МРа	ASTM D790
Flexural Strength	72.4	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	27	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	210	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	79.4	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm, RTP Tested)	НВ		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	210 to 288	°C	
Middle Temperature	210 to 288	°C	
Front Temperature	210 to 288	°C	

Mold Temperature	37.8 to 71.1	°C	
Injection Pressure	68.9 to 138	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

