# Arak LLDPE HD5050UA

#### High Density Polyethylene

### Shazand (Arak) Petrochemical Corporation

#### Message:

HD5050UA is an ultra-violet light stabilised high density polyethylene copolymergrade with a narrow molecular weight distribution, specially developed forinjection moulding applications where a good resistance to environmental stress cracking is required.

Characteristics:

Good environmental stress cracking resistance.

High impact resistance, especially at low temperatures.

Good weathering resistance.

Typical applications are:

Large dustbins & pails.

Pallet boxes.

Caps & closures.

Fish crates.

Technical parts.

\* HD5050UA is suitable for food contact.

General Information					
Additive	UV Stabilizer				
Features	Copolymer				
	Food Contact Acceptable				
	Good UV Resistance				
	Good Weather Resistance				
	High ESCR (Stress Crack Resist.)				
	High Impact Resistance				
	Low Temperature Impact Resistance				
	Narrow Molecular Weight Distribution				
Uses	Caps				
	Closures				
	Containers				
	Crates				
	Engineering Parts				
	Pails				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	0.950	g/cm³	ASTM D2838		
Melt Mass-Flow Rate (MFR) (190°C/2.16					
kg)	4.5	g/10 min	ASTM D1238		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D)	64		ASTM D2240		
Mechanical	Nominal Value	Unit	Test Method		

Tensile Strength (Yield)	25.0	MPa	ASTM D638
Tensile Elongation (Break)	1000	%	ASTM D638
Flexural Modulus	800	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	15	kJ/m²	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

