

Andur M-33 (94% 1,4BD/ 6% TMP)

Polyurethane (Polyester, MDI)
Anderson Development Company

Message:

Andur M-33 is a low melting MDI-Ester prepolymer that, when processed with close attention to handling procedures and formulation, produces high quality elastomers. These elastomers perform very well in low temperature applications.

General Information			
Forms	Liquid		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore A)	85		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Compressive Strength			ASTM D695
2% strain	0.517	MPa	ASTM D695
5% strain	1.14	MPa	ASTM D695
10% strain	2.07	MPa	ASTM D695
15% strain	3.00	MPa	ASTM D695
20% strain	4.00	MPa	ASTM D695
25% strain	5.00	MPa	ASTM D695
50% strain	14.2	MPa	ASTM D695
Taber Abrasion Resistance	24.3	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	6.83	MPa	ASTM D412
300% strain	12.3	MPa	ASTM D412
Tensile Strength (Yield)	39.9	MPa	ASTM D412
Tensile Elongation (Break)	480	%	ASTM D412
Compression Set	17	%	ASTM D395
Bayshore Resilience	40	%	ASTM D2632
Thermoset	Nominal Value	Unit	
Pot Life	6.0 - 8.0	min	
Demold Time	35	min	
Additional Information			

Die C Tear, ASTM D1004: 535 pliAverage Split Tear, ASTM D1938: 150 pliStoichiometry Curative Level: 97%NBS Abrasion: 250% Rubber StandardParts of curative per 100 parts Andur M-33, 6.75% NCO: 6.89 parts by weightParts of curative per 100 parts Andur M-33, 6.8% NCO: 6.94 parts by weightParts of curative per 100 parts Andur M-33, 6.85% NCO: 6.99 parts by weightParts of curative per 100 parts Andur M-33, 6.9% NCO: 7.04 parts by weightParts of curative per 100 parts Andur M-33, 6.95% NCO: 7.09 parts by weightParts of curative per 100 parts Andur M-33, 7% NCO: 7.14 parts by weightMix

Temperature:

Andur M-33: 176-194°F

Curative 1,4BD/TMP: 77-158°F

Stability:

Ambient Temperature, 25°C: 6 Months

Melting Temperature, 60°C: 1 Month

Processing Temperature, 90°C: 12 Hours

Processing Temperature, 105°C: 3 Hours

Injection	Nominal Value	Unit
Mold Temperature	80.0 - 120	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT