

Zytel® RS LCFG3060 NC010

RENEWABLY SOURCED™ POLYAMIDES*

DuPont Performance Polymers

Message:

Zytel® RS LCFG3060 NC010 is a RENEWABLY SOURCED™ POLYAMIDES* product. It can be processed by extrusion, profile extrusion, or sheet extrusion and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Sheet.

General Information				
Uses		Profiles		
		Sheet		
Forms		Pellets		
Processing Method		Extrusion		
		Profile Extrusion		
		Sheet Extrusion		
Part Marking Code (ISO 11469)		>PA610<		
Resin ID (ISO 1043)		PA610		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.07	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.5	--	%	
Flow	1.4	--	%	
Water Absorption				ISO 62
23°C, 24 hr, 2.00 mm	3.3	--	%	
Equilibrium, 23°C, 2.00 mm, 50% RH	1.4	--	%	
Viscosity Number	150	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2000	1200	MPa	ISO 527-2
Tensile Stress (Yield)	58.0	--	MPa	ISO 527-2
Tensile Strain (Yield)	5.0	--	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	--	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°C	8.7	--	kJ/m ²	
23°C	6.8	--	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	55.0	--	°C	ISO 75-2/A
Melting Temperature ¹	223	--	°C	ISO 11357-3
NOTE				

1.	10°C/min
----	----------

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT