# Polyrocks 8200EP95V

### Thermoplastic Elastomer

Polyrocks Chemical Co., Ltd

#### Message:

Thermoplastic halogen-free flame retardant TPE wire & cable compound is environmental halogen-free material with phosphorus and nitrogen as flame retardant elements. Carbonize and swelling mechanism play the flame retardant performance. Thermoplastic halogen-free flame retardant TPE wire & cable compound, which Mechanical properties meet the UL requirements of TPE wire and cable. The flammability reach UL1581 VW-1, Matt matte, low temperature resistance, PS/ABS migration resistance, no red phosphorus, and meet the requirements of ROHS, SVHC, PFOS & PFOA, 16P, Halogen-free, PAHs... etc.

General Information					
Additive	Flame retardancy 2				
Features	Low temperature resistance				
	Halogen-free				
	Flame retardancy				
Uses	Wire and cable applications				
	Wire sheath				
	Insulating material				
Wire Types (UL 1581)	VW-1				
Agency Ratings	EC 1907/2006 (REACH)				
RoHS Compliance	RoHS compliance				
Appearance	Rough surface polishing				
Forms	Particles				
Physical	Nominal Value	Unit			
Density	1.07	g/cm³			
Hardness	Nominal Value	Unit			
Durometer Hardness (Shore A)	95				
Elastomers	Nominal Value	Unit			
Tensile Strength	14.0	MPa			
Tensile Elongation (Break)	230	%			
Aging	Nominal Value	Unit			
Change in Tensile Strength in Air (136°C, 168 hr)	7.0	%			
Change in Ultimate Elongation in Air (136°C, 168 hr)	-20	%			
Thermal	Nominal Value	Unit			
Brittleness Temperature	< -40.0	°C			
Electrical	Nominal Value	Unit	Test Method		
Volume Resistivity (20°C)	9.1E+17	ohms·cm			
Dielectric Strength	28	kV/mm			

Flammability	Nominal Value	Unit	Test Method
Flame Rating (6.0 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

