

KOPLA PA6 KNG1030F

Polyamide 6

KOPLA Co., Ltd.

Message:

KOPLA PA6 KNG1030F is a Polyamide 6 (Nylon 6) material filled with glass fiber. It is available in Asia Pacific.

Important attributes of KOPLA PA6 KNG1030F are:

Flame Rated

Flame Retardant

Typical applications include:

Automotive

Electrical/Electronic Applications

Housings

General Information	
Filler / Reinforcement	Glass Fiber
Features	Flame Retardant
Uses	Automotive Interior Parts
	Electrical Parts
	Housings

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.60	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30 to 0.90	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.1	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	152	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	> 3.0	%	ASTM D638
Flexural Modulus (23°C)	8920	MPa	ASTM D790
Flexural Strength (23°C)	206	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	100	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	210	°C	
1.8 MPa, Unannealed	200	°C	
Melting Temperature	220	°C	
CLTE - Flow	3.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13 to 1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149

Dielectric Constant (1 MHz)	3.80		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

