

# Hostaform® S 9364

Acetal (POM) Copolymer

Celanese Corporation

## Message:

Hostaform® acetal copolymer grade S 9364 is highly impact modified grade for demanding applications. Hostaform® S 9364 provides a significant improvement in impact strength and flexibility over standard impact modified grades such as Hostaform® S 9063 and S 9064.

Chemical abbreviation according to ISO 1043-1: POM-HI

| General Information                         |                         |                        |                 |
|---------------------------------------------|-------------------------|------------------------|-----------------|
| UL YellowCard                               | E38860-100674465        |                        |                 |
| Additive                                    | Impact modifier         |                        |                 |
| Features                                    | Impact modification     |                        |                 |
|                                             | Impact resistance, good |                        |                 |
| RoHS Compliance                             | Contact manufacturer    |                        |                 |
| Resin ID (ISO 1043)                         | POM-HI                  |                        |                 |
| Physical                                    | Nominal Value           | Unit                   | Test Method     |
| Density                                     | 1.37                    | g/cm <sup>3</sup>      | ISO 1183        |
| Melt Volume-Flow Rate (MVR) (190°C/2.16 kg) | 4.00                    | cm <sup>3</sup> /10min | ISO 1133        |
| Molding Shrinkage                           |                         |                        | ISO 294-4       |
| Vertical flow direction                     | 1.5                     | %                      | ISO 294-4       |
| Flow direction                              | 1.6                     | %                      | ISO 294-4       |
| Water Absorption (Saturation, 23°C)         | 0.80                    | %                      | ISO 62          |
| Mechanical                                  | Nominal Value           | Unit                   | Test Method     |
| Tensile Modulus                             | 1650                    | MPa                    | ISO 527-2/1A/1  |
| Tensile Stress (Yield)                      | 43.0                    | MPa                    | ISO 527-2/1A/50 |
| Tensile Strain (Yield)                      | 16                      | %                      | ISO 527-2/1A/50 |
| Flexural Modulus (23°C)                     | 1550                    | MPa                    | ISO 178         |
| Impact                                      | Nominal Value           | Unit                   | Test Method     |
| Charpy Notched Impact Strength              |                         |                        | ISO 179/1eA     |
| -30°C                                       | 11                      | kJ/m <sup>2</sup>      | ISO 179/1eA     |
| 23°C                                        | 21                      | kJ/m <sup>2</sup>      | ISO 179/1eA     |
| Charpy Unnotched Impact Strength            |                         |                        | ISO 179/1eU     |
| -30°C                                       | No Break                |                        | ISO 179/1eU     |
| 23°C                                        | No Break                |                        | ISO 179/1eU     |
| Thermal                                     | Nominal Value           | Unit                   | Test Method     |
| Heat Deflection Temperature                 |                         |                        |                 |
| 0.45 MPa, not annealed                      | 140                     | °C                     | ISO 75-2/B      |
| 1.8 MPa, not annealed                       | 75.0                    | °C                     | ISO 75-2/A      |
| Melting Temperature <sup>1</sup>            | 166                     | °C                     | ISO 11357-3     |

| Linear thermal expansion coefficient |               |          | ISO 11359-2 |
|--------------------------------------|---------------|----------|-------------|
| Flow                                 | 1.2E-4        | cm/cm/°C | ISO 11359-2 |
| Lateral                              | 1.1E-4        | cm/cm/°C | ISO 11359-2 |
| Injection                            | Nominal Value | Unit     |             |
| Drying Temperature                   | 80.0 - 100    | °C       |             |
| Drying Time                          | 3.0           | hr       |             |
| Rear Temperature                     | 170 - 180     | °C       |             |
| Middle Temperature                   | 180 - 190     | °C       |             |
| Front Temperature                    | 180 - 190     | °C       |             |
| Nozzle Temperature                   | 180 - 200     | °C       |             |
| Processing (Melt) Temp               | 180 - 200     | °C       |             |
| Mold Temperature                     | 60.0 - 70.0   | °C       |             |
| Injection Pressure                   | 60.0 - 120    | MPa      |             |
| Injection Rate                       | Slow          |          |             |
| Holding Pressure                     | 60.0 - 120    | MPa      |             |
| Back Pressure                        | 0.00 - 0.500  | MPa      |             |
| Injection instructions               |               |          |             |
| Zone 4 Temperature: 180 to 200°C     |               |          |             |
| NOTE                                 |               |          |             |
| 1.                                   | 10°C/min      |          |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

