

Hanwha Total PE E220F

Ethylene Vinyl Acetate Copolymer
HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

E220F is a EVA (ethylene-vinylacetate copolymer) resin for crosslinked foam applications including mid-sole and in-sole of athletic shoes. This grade is designed to be processed in conventional kneading and rolling equipment for mixing and dispersing crosslinking agent and foaming agent.

General Information			
Features	Low compressive deformability		
	Copolymer		
	Dispersible		
	Workability, good		
	Crosslinkable		
	Good tear strength		
Uses	Electronic insulation		
	Composite		
	Foam		
	Footwear		
Forms	Particle		
Processing Method	Composite		
	Compression molding		
Physical	Nominal Value	Unit	Test Method
Density	0.944	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, F10)	500	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	90		ASTM D2240
Shaw D	35		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	28.4	MPa	ASTM D638
Tensile Elongation (Break)	800	%	ASTM D638
Apparent Bending Modulus	44.1	MPa	ASTM D747
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-70.0	°C	ASTM D746
Vicat Softening Temperature	55.0	°C	ASTM D1525 ¹

Melting Temperature	87.0	°C
Additional Information		
Kneader Temperature: 95 to 105 °C Foaming Temperature: 155 °C Foaming Pressure: 150 kg/cm ³ Curing Time: 40 min VA Content, SAMSUNG TOTAL: 22 kg force/cm ²		
NOTE		
1.	压力1 (10N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT