

ADEKA EH-5046S

Epoxy; Epoxide
Adeka Corporation

Message:
High adhesion, rapid curing at high temperature, high Tg

General Information			
Features	Fast Cure		
	Good Adhesion		
Physical	Nominal Value	Unit	
Particle Size - (d50)	5.00	μm	
Composition	20 to 25	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	160	°C	ASTM E1356
Melting Temperature	120 to 125	°C	
Uncured Properties	Nominal Value	Unit	
Gel Time (150°C)	0.66	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT