

TECHNYL® B 238 BLACK 21 N

Polyamide 66/6 Copolymer
Solvay Engineering Plastics

Message:

Unreinforced and modified copolyamide 66/6, heat stabilized, with improved impact resistance, for injection moulding.

General Information				
Additive	Heat Stabilizer			
Features	Good Impact Resistance			
	Heat Stabilized			
Uses	Automotive Applications			
	Automotive Under the Hood			
Appearance	Black			
Processing Method	Injection Molding			
Part Marking Code (ISO 11469)	>PA66/6<			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.09	--	g/cm ³	ISO 1183/A
Molding Shrinkage				Internal Method
Across Flow	2.1	--	%	
Flow	2.2	--	%	
Water Absorption (23°C, 24 hr)	1.4	--	%	ISO 62
Molding Shrinkage Isotropy	1.07	--		Internal Method
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2300	900	MPa	ISO 527-2/1A
Tensile Stress				ISO 527-2/1A
Yield	60.0	40.0	MPa	
Break	50.0	40.0	MPa	
Tensile Strain				ISO 527-2/1A
Yield	5.0	12	%	
Break	50	250	%	
Flexural Modulus	2000	700	MPa	ISO 178
Flexural Stress	80.0	27.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	8.0	30	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break	No Break		ISO 179/1eU

Notched Izod Impact Strength	7.0	18	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	62.0	--	°C	ISO 75-2/Af
Melting Temperature	242	--	°C	ISO 11357-3
CLTE - Transverse (23 to 85°C)	7.0E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	5.0E+14	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+14	1.0E+12	ohms·cm	IEC 60093
Electric Strength	32	30	kV/mm	IEC 60243-1
Dissipation Factor	0.020	0.070		IEC 60250
Comparative Tracking Index				IEC 60112
Solution A	500	500	V	
Solution B	475	--	V	
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
Oxygen Index	21	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	240 to 250		°C	
Middle Temperature	250 to 260		°C	
Front Temperature	260 to 270		°C	
Mold Temperature	60.0 to 80.0		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT