

Ekalon® 20 E I S

Polycarbonate

Sattler KunststoffWerk GmbH

Message:

Ekalon® 20 E I S is a polycarbonate (PC) product. It is available in Europe. The main characteristics are: flame retardant/rated flame.

General Information			
UL File Number	E178422		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ISO 1133
Molding Shrinkage	0.60	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ISO 527-2
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Tensile Strain (Yield)	50	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	20	kJ/m²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	135	°C	ISO 306/B50
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Additional Information			

Melt Mass Flow Rate (MFR), ISO 1133, 300 °C/1.2kg: 17 to 23 g/10 min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT