Gallonprene® GP520-7016

Thermoplastic Elastomer

Shenzhen Sungallon Rubber & Plastic Corporation Limited

Message:

Gallonprene® GP520-7016 is a thermoplastic elastomer (TPE) product. It can be processed by injection molding and is available in Africa and the Middle East, Latin America or Asia Pacific. Gallonprene® GP520-7016 application areas include engineering/industrial accessories, electrical/electronic applications, household applications and sporting goods.

Features include: Comply with REACH standard ROHS certification Halogen-free

General Information					
Features	High elasticity				
	Halogen-free				
Uses	overmolding				
	Plug				
	Household goods				
	Connector				
	Sporting goods				
Agency Ratings	EC 1907/2006 (REACH)				
RoHS Compliance	RoHS compliance				
Appearance	White				
	Rough surface polishing				
Processing Method	Injection molding				
Physical Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.06	g/cm³	ASTM D792		
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	35	g/10 min	ASTM D1238		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A, 23°C)	70	Offic	ASTM D2240		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Strength ¹ (Break)	10.5	MPa	ASTM D412		
Tensile Elongation ² (Break)	700	%	ASTM D412		
Injection	Nominal Value	Unit	7,011112		
Rear Temperature	120 - 140	°C			
Middle Temperature	130 - 150	°C			
Front Temperature	140 - 160	°C			
Processing (Melt) Temp	110 - 130	°C			
5 (- 7 - F	30.0 - 60.0	°C			

Injection Rate	Moderate			
	<u> </u>	<u> </u>	<u> </u>	

Injection instructions

Processing Temperature Limit: 260°CInjection Pressure: ModerateBack Pressure: 20 to 50%Overmolding Parameters:Rear Temperature: 150 to 170°CCenter Temperature: 160 to 180°CFront Temperature: 170 to 190°CMelt Temperature: 110 to 130°CMold Temperature: 30 to 60°CProcessing Temperature Limit: 260°CInjection Pressure: ModerateInjection Speed: ModerateBack Pressure: 20 to 50%

NOTE		
1.	500 mm/min	
2.	500 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

