

COPYLENE® CH023NX

Polypropylene Homopolymer

Phillips 66

Message:

COPYLENE® CH023NX has a high performance nucleation system designed to yield high clarity thermoformed articles.

Applications:

Thermoforming

General Information			
Additive	Nucleating Agent		
Features	High Clarity		
	Homopolymer		
	Nucleated		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.902	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.3	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	36.8	MPa	ASTM D638
Tensile Elongation (Yield)	7.8	%	ASTM D638
Flexural Modulus - 1% Secant ²	1690	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	90	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	114	°C	ASTM D648
NOTE			
1.	50 mm/min		
2.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

