

SABIC® LDPE HP0823J

Low Density Polyethylene

SABIC Americas, Inc.

Message:

PRODUCT DESCRIPTION:

SABIC® LDPE HPO823J is a Low Density Polyethylene grade formulated with slip and anti-block additives. It typically exhibits good melt strength with good draw down ability. Films typically exhibit good toughness and good biaxial shrink properties with low friction and low blocking.

TYPICAL APPLICATIONS:

Shrink film, thin industrial film, thin packaging film, bags & pouches. This grade enables high speed converting without sticking. This product is not intended for use in medical and pharmaceutical applications.

General Information			
Additive	Anti-caking agent (900 ppm) 2		
	Sliding agent (500 ppm) 3		
Features	Low density		
	Low friction coefficient		
	smoothness		
	Anti-caking property		
	Good stripping		
	Good melt strength		
	Good toughness		
	Compliance of Food Exposure		
Uses	Packaging		
	Films		
	Bags		
	Industrial application		
	Shrinkable film		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.923	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.80	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (0.0500 mm)	260	MPa	ISO 527-2
Tensile Stress (yield, 0.0500mm)	11.0	MPa	ISO 527-2
Coefficient of Friction		%	ISO 8295
Blow-up Ratio	2.50 - 4.00		
Films	Nominal Value	Unit	Test Method

Film Thickness - Tested	50	μm	
Film Thickness - Recommended / Available	25 - 80 micron		
Tensile Stress			ISO 527-3
MD: Broken, 50 μm, blown film	24.0	MPa	ISO 527-3
TD: Broken, 50 μm, blown film	22.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Broken, 50 μm, blown film	300	%	ISO 527-3
TD: Broken, 50 μm, blown film	600	%	ISO 527-3
Dart Drop Impact (50 μm, Blown Film)	150	g	ASTM D1709
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	96.0	°C	ISO 306/A50
Melting Temperature (DSC)	111	°C	ISO 3146
Optical	Nominal Value	Unit	Test Method
Gloss			ASTM D2457
20, 50.0 μm, blown film	> 40		ASTM D2457
60, 50.0 μm, blown film	> 90		ASTM D2457
Haze (50.0 μm, Blown Film)	< 9.0	%	ASTM D1003
Additional Information	Nominal Value		
Measured on 50 micron thickness blown film extruded at melt temperature of 180°C with BUR of 2.5			
Extrusion	Nominal Value	Unit	
Melt Temperature	170 - 220	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT