

KumhoSunny PC 2502NH

Polycarbonate

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

PC2502NH is balance peformance and 1.6mm V-0 flame retardant non-halogenand PC resin. It has excellent UV stability. PC2502NH is mainly used in monitor housings,LCD, household electric product, etc.

General Information			
UL YellowCard	E254819-497297		
Features	Flame Retardant		
	Good UV Resistance		
	Halogen Free		
Uses	Electrical/Electronic Applications		
	Household Goods		
	Housings		
	LCD Applications		
UL File Number	E254819		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	62.0	MPa	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	2100	MPa	ASTM D790
Flexural Strength	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	580	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	120	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	

Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	230 to 250	°C
Middle Temperature	250 to 270	°C
Front Temperature	270 to 280	°C
Nozzle Temperature	260 to 280	°C
Processing (Melt) Temp	240 to 280	°C
Mold Temperature	60.0 to 100	°C
Back Pressure	0.200 to 0.800	MPa
Screw Speed	20 to 80	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

