

Elvax® 150W

Ethylene Vinyl Acetate Copolymer

DuPont Packaging & Industrial Polymers

Message:

DuPont™ Elvax® 150W is an ethylene-vinyl acetate copolymer resin for use in industrial applications. This resin is supplied in pellet form and contains a "W" amide additive to improve pellet handling.

Composition

32 % By Weight Vinyl Acetate comonomer content

Contains a "W" amide additive to improve pellet handling.

Thermal Stabilizer: BHT antioxidant

Applications

Elvax® resins can be used in a variety of applications involving molding, compounding, extrusion, adhesives, sealants, and wax blends. For additional information and properties associated with specific applications, please refer to the Grade Selector Guides found on the Elvax® website for industrial applications. http://www2.dupont.com/Elvax/en_US/tech_info/index.html

General Information			
Additive	Antioxidant		
	Heat Stabilizer		
Features	Antioxidant		
	Copolymer		
	Food Contact Acceptable		
	Heat Stabilized		
Uses	Adhesives		
	Blending		
	Compounding		
	Industrial Applications		
	Sealants		
	Wire Jacketing		
Agency Ratings	FDA 21 CFR 177.1350(a)(1)		
Forms	Pellets		
Processing Method	Blow Molding		
	Compounding		
	Compression Molding		
	Extrusion		
	Injection Molding		
	Sheet Extrusion		
Physical	Structural Foam Molding		
	Nominal Value	Unit	Test Method
	Specific Gravity	0.957	g/cm ³
			ASTM D792, ISO 1183

Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	43	g/10 min	ASTM D1238, ISO 1133
Vinyl Acetate Content	32.0	wt%	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	36.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	63.0	°C	ASTM D3418, ISO 3146
Injection	Nominal Value	Unit	
Processing (Melt) Temp	< 230	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	< 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

