

Mediprene® 880161

Styrene Butadiene Styrene Block Copolymer

ELASTO

Message:

Preliminary datasheet
Mediprene® 880161: Thermoplastic Elastomer
Basic material: TPS-SBS
Hardness: 50 Shore A (4 mm)
Service temperature range: -50 -- +75°C (unstressed material)
Colour: Transparent, but can be available in any colour.
Presentation: Free flowing pellets that can be processed without predrying, when stored under normal conditions.
Weather Resistance: Moderate
Chemical Resistance: Good (excluding organic solvents, aromatic- and vegetable oils)
Recycling: 100% recyclable
Special Features: The material is based on medically approved raw materials.

General Information			
Features	Good Chemical Resistance		
	Good Processability		
	Good Weather Resistance		
	Recyclable Material		
Uses	Medical/Healthcare Applications		
Appearance	Clear/Transparent		
	Colors Available		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	20	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 4.00 mm)	50		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ASTM D638
100% Secant	0.900	MPa	
300% Secant	2.00	MPa	
Tensile Strength	10.0	MPa	ASTM D638
Tensile Elongation (Break)	900	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	65.0	kN/m	ASTM D624

Thermal	Nominal Value	Unit
Service Temperature	-50 to 75	°C
Injection	Nominal Value	Unit
Rear Temperature	170 to 200	°C
Middle Temperature	170 to 200	°C
Front Temperature	170 to 200	°C
Mold Temperature	10.0 to 40.0	°C
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	150 to 190	°C
Cylinder Zone 2 Temp.	150 to 190	°C
Cylinder Zone 3 Temp.	150 to 190	°C
Cylinder Zone 4 Temp.	150 to 190	°C
Cylinder Zone 5 Temp.	150 to 190	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

