

QR Resin QR-5000-GF30

Polyether Imide

QTR, Inc.

Message:

QR Resin QR-5000-GF30 is a Polyether Imide (PEI) product filled with 30% glass fiber. It is available in North America.

Characteristics include:

Chemical Resistant

Heat Resistant

High Stiffness

High Strength

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Chemical Resistance		
	High Heat Resistance		
	High Stiffness		
	High Strength		
Appearance	Colors Available		
	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.20 to 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	155	MPa	ASTM D638
Flexural Modulus	8270	MPa	ASTM D790
Flexural Strength (Yield)	207	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	216	°C	
1.8 MPa, Unannealed	210	°C	
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0 to 6.0	hr	
Drying Time, Maximum	6.0	hr	
Rear Temperature	343 to 366	°C	
Middle Temperature	354 to 377	°C	
Front Temperature	366 to 388	°C	

Nozzle Temperature	360 to 382	°C
Processing (Melt) Temp	366 to 388	°C
Mold Temperature	135 to 163	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

