

TES J-1200/30/VO/Natl

Acrylonitrile Butadiene Styrene

Techmer Engineered Solutions

Message:

TES J-1200/30/VO/Natl is an Acrylonitrile Butadiene Styrene (ABS) product filled with 30% glass fiber. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

- Flame Rated
- RoHS Compliant
- Flame Retardant
- Good Dimensional Stability
- Impact Resistant

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
	Good Dimensional Stability		
	Good Impact Resistance		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.060 to 0.13	%	ASTM D955
Water Absorption (24 hr)	0.21	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	64		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6000	MPa	ASTM D638
Tensile Strength (Yield)	91.7	MPa	ASTM D638
Tensile Elongation (Yield)	2.7	%	ASTM D638
Flexural Modulus	7240	MPa	ASTM D790
Flexural Strength (Yield)	114	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	107	°C	
1.8 MPa, Unannealed	101	°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	

Drying Time	2.0 to 16	hr
Rear Temperature	210 to 227	°C
Middle Temperature	216 to 232	°C
Front Temperature	204 to 216	°C
Nozzle Temperature	193 to 216	°C
Processing (Melt) Temp	227 to 254	°C
Mold Temperature	65.6 to 82.2	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT