X-Pro SP 200 TF 13 3325

Polypropylene Copolymer

CTC Plastics, LLC

Message:

CTC Plastics manufactures resins up to 99% recycled making them a lower cost alternative to virgin resins, while maintaining comparable quality and process ability. Clients can purchase resins directly to meet specifications or request CTC Plastics to create a custom resin from either of our two facilities. Our resins are customized per batch depending on compound needs. Different formulas can enhance strength, durability or flexibility. With our onsite certified lab, we are able to personalize the compound to your exact needs. Recycled resins lower cost, meet your exact specifications and reduce dependency on foreign oil by over 10 million gallons per year.

Description: General purpose, medium flow, Polypropylene copolymer

Applications: Automotive, Industrial, Construction, Consumer, Lawn & Garden products, general purpose applications Color: General Purpose Black

General Information				
Recycled Content	Yes			
Features	Copolymer			
	Medium liquidity			
	General			
Uses	Lawn and Garden Equipment			
	Industrial application			
	Architectural application field			
	Application in Automobile Field			
	General			
	Consumer goods application field			
Appearance	Black			
Processing Method				
-	Injection molding	Unit	Taat Mathad	
Physical	Nominal Value	Unit	Test Method	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10 - 20	g/10 min	ASTM D1238, ISO 1133	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield)	13.8	MPa	ASTM D638, ISO 527-2	
Flexural Modulus ¹	689	MPa	ASTM D790, ISO 178	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C)	160	J/m	ISO 180, ASTM D256	
Injection	Nominal Value	Unit		
Drying Temperature	82.2	°C		
Drying Time	2.0 - 4.0	hr		
Rear Temperature	182 - 216	°C		
Middle Temperature	193 - 227	°C		
Front Temperature	204 - 216	°C		
Nozzle Temperature	204 - 216	°C		

Processing (Melt) Temp	204 - 216	°C	
Mold Temperature	26.7 - 60.0	°C	
Injection Pressure	3.45 - 10.3	MPa	
Clamp Tonnage	2.8 - 3.4	kN/cm ²	
Injection instructions			
Screw Speed: Medium to Fast			
NOTE			
1.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

