

ALTECH® PA6 A 3030/220 GB30 UV

Polyamide 6
ALBIS PLASTIC GmbH

Message:

ALTECH®PA6 A 3030/220 GB30 UV is a polyamide 6 (nylon 6) product containing 30% glass beads. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region.

Features include:

- Comply with REACH standard
- ROHS certification
- heat stabilizer
- excellent release agent
- UV stability

General Information			
Filler / Reinforcement	Glass beads, 30% filler by weight		
Additive	heat stabilizer		
	UV stabilizer		
Features	Thermal Stability		
	Good demoulding performance		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3150	MPa	ISO 527-2
Tensile Stress (Break)	50.0	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	3150	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	23	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	59.0	°C	ISO 75-2/A
Vicat Softening Temperature	171	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	80	°C	
Drying Time	2.0 - 12	hr	
Processing (Melt) Temp	260 - 280	°C	

Mold Temperature

80 - 100

°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

