

Bergamid™ A700 G15 HW UF NC099

Polyamide 66

PolyOne Corporation

Message:

Glass fiber reinforced PA66 compound with flame retardant.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Features	Phosphorus content, low (to none)		
	Heat resistance, high		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.32	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.60 - 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	110	MPa	ISO 527-2/5
Flexural Modulus ¹	6700	MPa	ISO 178
Flexural Stress ²	180	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³ (1.8 MPa, Unannealed)	230	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.6 mm)	V-0		Internal method
Injection	Nominal Value	Unit	
Drying Temperature	80 - 90	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	260 - 280	°C	
Middle Temperature	260 - 280	°C	
Front Temperature	260 - 280	°C	
Mold Temperature	65 - 85	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			
1.	2.0 mm/min		

2.	2.0 mm/min
3.	3.2mm thickness

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

