

PERCOM® KHT40

Polypropylene Homopolymer

A. Schulman Europe

Message:

PERCOM® KHT40 is a Polypropylene Homopolymer (PP Homopolymer) material filled with 40% talc. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of PERCOM® KHT40 are:

Flame Rated

RoHS Compliant

Homopolymer

Typical application of PERCOM® KHT40: Appliances

General Information			
Filler / Reinforcement	Talc,40% Filler by Weight		
Features	Homopolymer		
Uses	Appliance Components		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 1.1	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	66		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	34.0	MPa	ISO 527-2
Flexural Modulus	4500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	3.0	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	130	°C	ISO 75-2/B
1.8 MPa, Unannealed	88.0	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

