

# Aropol™ MR 14029

Thermoset Polyester

Ashland Performance Materials

## Message:

Ashland Resins for the Pultrusion Market  
Chemistry  
High reactivity UPR  
Performance Attributes  
Premier weathering performance. Process friendly.  
Typical Applications  
Exterior shapes. UV resistant parts. Cable trays. Ladder rails.

General Information		
Features	Good Processability	
	Good UV Resistance	
	Good Weather Resistance	
	High Reactivity	
Uses	Electrical/Electronic Applications	
Processing Method	Pultrusion	
Physical	Nominal Value	Unit
Solution Viscosity	2500	mPa · s
Mechanical	Nominal Value	Unit
Tensile Modulus	3650	MPa
Tensile Strength	68.9	MPa
Tensile Elongation (Break)	2.4	%
Flexural Modulus	3590	MPa
Flexural Strength	112	MPa
Thermal	Nominal Value	Unit
Heat Deflection Temperature	148	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT