

Buna® EP T 2460

Ethylene Propylene Diene Terpolymer
LANXESS Corporation

Message:

Ethylene-propylene-diene rubber (EPDM), with ethylidene norbornene (ENB) as diene; amorphous; very low viscosity.

General Information			
Features		Low viscosity amorphous	
Forms		bag	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.858	g/cm ³	ASTM D792
Mooney Viscosity (ML 1+8, 100°C)	27 - 39	MU	ASTM D1646
Ethylene Content	58.0 - 66.0	wt%	ASTM D3900
Ethylidene Norbornene (ENB) Content	3.4 - 4.6	wt%	ASTM D6047
Additional Information			

Total Ash, ISO 247/ASTM D5667: <0.5%Stabilizer: Non-stainingVolatile Matter, ISO 248/ASTM D5668: <0.75 wt%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

