

QR Resin QR-1000-GF20

Polycarbonate

QTR, Inc.

Message:

Available with UV (V) or Release (R).

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Toughness		
Appearance	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10 to 20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.20	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	110	MPa	ASTM D638
Flexural Modulus	5380	MPa	ASTM D790
Flexural Strength (Yield)	130	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	960	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	149	°C	
1.8 MPa, Unannealed	146	°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 6.0	hr	
Drying Time, Maximum	6.0	hr	
Rear Temperature	282 to 310	°C	
Middle Temperature	293 to 316	°C	
Front Temperature	304 to 327	°C	
Nozzle Temperature	304 to 321	°C	
Processing (Melt) Temp	304 to 327	°C	
Mold Temperature	82.2 to 116	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

