

Ecomass® 1050ZD96

Polyamide

Ecomass Technologies

Message:

Ecomass® 1050ZD96 is a polyamide material that contains a tungsten filler. This product is available in North America and is processed by injection molding.

Ecomass® The main features of 1050ZD96 are:

Good toughness

non-toxic

General Information			
Filler / Reinforcement	Tungsten packing		
Features	High density		
	Good toughness		
	Non-toxic		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	9.98	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 - 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6450	MPa	ASTM D638
Tensile Strength	34.5	MPa	ASTM D638
Tensile Elongation (Break)	1.7	%	ASTM D638
Flexural Modulus	5000	MPa	ASTM D790
Flexural Strength	49.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	135	°C	ASTM D648
1.8 MPa, not annealed	121	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	0.25	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	73.9	°C	
Drying Time - Desiccant Dryer	4.0	hr	
Processing (Melt) Temp	204 - 254	°C	
Mold Temperature	57.2 - 85.0	°C	
Injection Rate	Moderate-Fast		

Back Pressure	0.103 - 0.172	MPa
Screw Speed	100 - 250	rpm
Clamp Tonnage	3.4 - 5.5	kN/cm ²
Cushion	6.35 - 12.7	mm
Screw L/D Ratio	20.0:1.0	
Screw Compression Ratio	2.5:1.0	

Injection instructions

Pack (Hold) Pressure: 65 to 75% of Injection Pressure
 Fill Time: 1.0 to 2.0 in/sec
 Pack (Hold) Time: 10 to 15 sec
 Cooling Time: As required
 Feed Throat: Cooled
 Nozzle Type: Reverse Taper
 Check Type: Free Flow
 Maximum Drying Temp: 200 °F
 Dryer Dew Point: -20 to -40 °F
 Minimum Air Flow: 0.8 to 1.0 CFM
 Injection Pressure: As Required

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

