## Hostacom TRC 787N E C11323

## Polypropylene Copolymer

LyondellBasell Industries

## Message:

Hostacom TRC 787N E is a 20% talc filled PP copolymer, with excellent impact/stiffness balance, good processability, high scratch resistance and good surface appearance. This grade is delivered in customer customized colors.

For regulatory compliance information, see Hostacom TRC 787N E C11323 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS). This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Rigid, good		
	Copolymer		
	High scratch resistance		
	Impact resistance, good		
	Workability, good		
	Scratch resistance		
	Good appearance		
Uses	Application in Automobile Field		
	Car interior equipment		
Appearance	Available colors		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.04	g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	21	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	18.0	MPa	ISO 527-2
Flexural Modulus <sup>1</sup> (23°C)	1850	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	6.6	kJ/m²	ISO 180/1A
23°C	48	kJ/m²	ISO 180/1A
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

