

# Di-Pak™ R-4528/17

Thermoplastic

Hapco Inc.

Message:

RIGID  
DI-PAK R-4528 Series

A black, flame retardant, thermally conductive, high performance series that can be used in all types of electrical components. Combined with its ability to dissipate heat, DI-PAK R-4528 also provides low linear thermal expansion, low shrinkage, and low exothermic heat while curing. Meets UL requirements.

General Information			
Features	Electrically Insulating		
	Flame Retardant		
	Good Processability		
	Good Toughness		
	High Heat Resistance		
	Low Shrinkage		
	Low Viscosity		
	Thermally Conductive		
Uses	Battery Cases		
	Electrical/Electronic Applications		
	Power Cable Shields		
	Switches		
Appearance	Black		
Forms	Liquid		
Processing Method	Encapsulating		
	Potting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.59	g/cm <sup>3</sup>	ASTM D4669
Molding Shrinkage - Flow	0.050 to 0.10	%	ASTM D2566
Weight - per cubic inch	26	g	
Service Temperature	85	°C	
Gel Time <sup>1</sup> (25°C)	40.0 to 60.0	min	ASTM D2971
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	88		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2140	MPa	ASTM D638
Tensile Strength	44.8	MPa	ASTM D638
Tensile Elongation (Break)	1.7	%	ASTM D638

Flexural Modulus	2250	MPa	ASTM D790
Flexural Strength	50.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	31	J/m	ASTM D256
Unnotched Izod Impact	42	J/m	ASTM D256
Thermal	Nominal Value	Unit	
Thermal Conductivity	0.39	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	7.3E+13	ohms·cm	ASTM D257
Dielectric Strength	25	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
1 kHz	3.60		
100 kHz	3.30		
Dissipation Factor (25°C, 100 kHz)	0.022		ASTM D150
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Part A	Mix Ratio by Weight: 100, Mix Ratio by Volume: 100		
Part B	Mix Ratio by Weight: 16, Mix Ratio by Volume: 30		
Thermoset Mix Viscosity (25°C)	4050	cP	ASTM D4878
Demold Time (21°C)	1400	min	
NOTE			
1.	100 g		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

