

Durethan® AM 430 H2.0 901510

Polyamide 66

LANXESS GmbH

Message:

PA 66, 30% mineral, injection molding, heat-aging stabilized

General Information				
Filler / Reinforcement		Mineral,30% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.39	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Across Flow : 290°C, 2.00 mm ¹	1.2	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.30	--	%	
Flow : 290°C, 2.00 mm ³	1.0	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.20	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	4800	2000	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	80.0	40.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	4.0	50	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	4900	2100	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain,23°C	130	50.0	MPa	
23°C ⁶	140	60.0	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	5.0	7.5	%	ISO 178/A
ISO Shortname	PA 66, GHR, 14-050, MD30	--		ISO 1874
Residual Moisture Content	0.030 to 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	< 10	< 10	kJ/m ²	
23°C	< 10	< 10	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	--	kJ/m ²	
23°C	70	120	kJ/m ²	

Notched Izod Impact Strength				ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	
23°C	< 10	< 10	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	50	--	kJ/m ²	
23°C	60	110	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	90.0	--	°C	ISO 75-2/A
Vicat Softening Temperature	244	--	°C	ISO 306/B120
Melting Temperature ⁸	262	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	6.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	--	cm/cm/°C	
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	280 to 300		°C	
Mold Temperature	80.0 to 120		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT