

CENUSIL® R 150

Silicone
Wacker Chemie AG

Message:
Silicone Rubber, HTV
Sealant Profiles, Construction

General Information			
Features	General Purpose		
	Low Compression Set		
Uses	Automotive Applications		
	Compounding		
Processing Method	Compression Molding		
	Press Molding		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Translucent		
Density	1.15	g/cm ³	DIN 51757
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	50		DIN 53505
Tensile Strength	8.00	MPa	DIN 53504
Tensile Elongation at Break	280	%	DIN 53504
Compression Set	10	%	DIN ISO 815-B
Tear Strength	12.0	kN/m	ASTM D624B
Rebound Resilience	70	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT