# Spartech Polycom 6070G100

### Polypropylene Homopolymer

#### Spartech Polycom

#### Message:

Spartech Polycom 6070G100 is a polypropylene homopolymer (PP Homopoly) product, which contains 20% talc filler. It is available in North America. Features include: odorless/tasteless channel Good processability Homopolymer Good stiffness

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Rigid, good		
	Homopolymer		
	Workability, good		
	The smell is low to none		
	The smell is low to none		
Appearance	White		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	1.5	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	31.7	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield, 23°C	4.0	%	ASTM D638
Fracture, 23°C	30	%	ASTM D638
Flexural Modulus - Tangent (23°C)	2410	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	27	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	118	°C	ASTM D648
1.8 MPa, not annealed	68.3	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

