

# Baydur® 728 IBS (35 pcf)

Polyurethane (MDI)

Covestro - PUR

## Message:

Baydur 728 IBS is a high-density polyurethane structural foam system used in the reaction injection molding (RIM) process. This system incorporates a specially engineered interactive blowing system (IBS) and internal mold release (IMR). The system is supplied as two reactive liquid components. Component A is a polymeric diphenylmethane diisocyanate (PMDI) and Component B is a formulated polyol system containing no CFC- or HCFC-blowing additives.

Baydur 728 IBS system is used in applications requiring a UL94 flammability rating of V-0 and/or 5VA for use in electronic, equipment housing, and appliance markets. The applications typically take advantage of the material's strength, excellent surface finish, and large-part capability. As with any product, use of the Baydur 728 IBS system in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

General Information			
UL YellowCard	E61384-475117	E61384-475574	
Additive	Blowing Agent		
	Mold Release		
Features	Good Strength		
	Good Surface Finish		
Uses	Appliances		
	Electrical/Electronic Applications		
	Housings		
Processing Method	Reaction Injection Molding (RIM)		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 6.35 mm)	13.1	MPa	ASTM D638
Tensile Elongation (Break, 6.35 mm)	8.0	%	ASTM D638
Flexural Modulus (6.35 mm)	814	MPa	ASTM D790
Flexural Strength (6.35 mm)	26.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength <sup>1</sup>	13	kJ/m²	Internal Method
Notched Izod Impact (6.35 mm)	11	J/m	ASTM D256
Unnotched Izod Impact (6.35 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 6.35 mm)	71.0	°C	ASTM D648
CLTE - Flow (70°C, 6.35 mm)	1.1E-4	cm/cm/°C	ASTM D696
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

