# Osterlene® LLDO-.9-918

### Linear Low Density Polyethylene

### Osterman & Company

### Message:

LLDO-.9-918 has features for easy processability, high toughness and strength and excellent seal properties.

LLDB-.9-918 meets the requirements of the Food and Drug Administration, 21 CFR Section 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations may apply.

General Information			
Features	Food Contact Acceptable		
	Good Toughness		
	High Strength		
Uses	Film		
	Non-specific Food Applications		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.920	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Secant Modulus - 1% Secant, MD	175	МРа	ASTM D882
Tensile Strength - MD			ASTM D882
Yield	10.0	МРа	
Break	48.0	MPa	
Tensile Elongation - MD (Break)	480	%	ASTM D882
Dart Drop Impact <sup>1</sup>	270	g	ASTM D1709A
Elmendorf Tear Strength - MD	420	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	59		ASTM D2457
Haze	10	%	ASTM D1003
NOTE			
1.	F50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

