

SureSpec HP-200NA

Polypropylene Homopolymer

Genesis Polymers

Message:

HP-200NA is a Nucleated Polypropylene certified prime resin designed for injection molding of thin-walled lightweight articles. HP-200NA contains antistatic and combines a good balance of medium-high flow processability with high contact clarity, short cycling, high stiffness, good tensile strength and excellent ESCR. HP-200NA recommended processing temperature is between 220° to 240°C with mold at 20°-50°C. HP-200NA complies with FDA regulation 21CFR 177.1520 and with most international regulations concerning the use of Polypropylene in contact with food.

General Information			
Additive	Antistatic		
	Nucleating Agent		
Features	Antistatic		
	Contact Clarity		
	Fast Molding Cycle		
	Food Contact Acceptable		
	High ESCR (Stress Crack Resist.)		
	High Flow		
	High Stiffness		
	High Tensile Strength		
	Homopolymer		
	Nucleated		
Uses	Thin-walled Parts		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	96		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	37.2	MPa	ASTM D638
Tensile Elongation ² (Yield)	11	%	ASTM D638
Flexural Modulus - 1% Secant ³	1860	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	32	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed)	123	°C	ASTM D648
Vicat Softening Temperature	154	°C	ASTM D1525
Injection	Nominal Value	Unit	
Processing (Melt) Temp	220 to 240	°C	
Mold Temperature	20.0 to 50.0	°C	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

