

Heraflex® HP 40-21-60

Styrene Ethylene Butylene Styrene Block Copolymer

Radici Plastics

Message:

TPS-SEBS Thermoplastic Elastomer. 40 Shore A. Good adhesion to polar materials. Application examples: Sealing ring for housing cover

General Information			
Features	Good Adhesion		
Uses	Seals		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	40		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	0.900	MPa	
300% Strain	1.60	MPa	
Tensile Stress (Break)	4.50	MPa	ISO 37
Tensile Elongation (Break)	> 300	%	ISO 37

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

