Petrothene® GA501041

Linear Low Density Polyethylene LyondellBasell Industries

Message:

The PETROTHENE GA 501 series of resins is pelletized linear low density polyethylene for film extrusion applications that require excellent drawdown and toughness. These resins have excellent puncture resistance, elongation and heat seal strength. Applications include heavy duty shipping sacks, prime liners, commercial and industrial packaging, as well as food and consumer packaging.

| General Information | | | | | |
|---------------------------------------|-------------------------|----------|-------------|--|--|
| Additive | Medium Antiblock | | | | |
| Features | Food Contact Acceptable | | | | |
| | Good Drawdown | | | | |
| | Good Heat Seal | | | | |
| | High Elongation | | | | |
| | Low Density | | | | |
| | Puncture Resistant | | | | |
| | Ultra High Toughness | | | | |
| Uses | Consumer Applications | | | | |
| | Food Packaging | | | | |
| | Heavy-duty Bags | | | | |
| | Industrial Applications | | | | |
| | Liners | | | | |
| | Packaging | | | | |
| | | | | | |
| Agency Ratings | FDA 21 CFR 177.1520 | | | | |
| Forms | Pellets | | | | |
| Processing Method | Film Extrusion | | | | |
| Physical | Nominal Value | Unit | Test Method | | |
| Density | 0.918 | g/cm³ | ASTM D1505 | | |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 | | | | | |
| kg) | 1.0 | g/10 min | ASTM D1238 | | |
| Films | Nominal Value | Unit | Test Method | | |
| Film Thickness - Tested | 25 | μm | | | |
| Secant Modulus | | | ASTM D882 | | |
| 1% Secant, MD : 25 μm | 186 | MPa | | | |
| 1% Secant, TD : 25 μm | 193 | MPa | | | |
| Tensile Strength | | | ASTM D882 | | |
| MD : Break, 25 μm | 45.5 | MPa | | | |
| TD : Break, 25 µm | 32.4 | MPa | | | |
| Tensile Elongation | | | ASTM D882 | | |

| MD : Break, 25 μm | 580 | % | |
|-----------------------------|---------------|------|-------------|
| TD : Break, 25 µm | 730 | % | |
| Dart Drop Impact (25 μm) | 100 | g | ASTM D1709A |
| Elmendorf Tear Strength | | | ASTM D1922 |
| MD : 25 μm | 130 | g | |
| TD : 25 µm | 330 | g | |
| Thermal | Nominal Value | Unit | Test Method |
| Vicat Softening Temperature | 107 | °C | ASTM D1525 |
| Optical | Nominal Value | Unit | Test Method |
| Haze (25.4 μm) | 20 | % | ASTM D1003 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

