

Alcryn® 2095 BK

Melt Processable Rubber

Advanced Polymer Alloys

Message:

Alcryn® 2095 BK is a melt processable rubber (MPR) material. This product is available in North America, Europe or Asia Pacific. The processing methods are: blow molding, extrusion, compression molding or injection molding.

Alcryn®The main features of 2095 BK are:

Comply with WEEE standard

ROHS certification

high liquidity

Good UV resistance

good weather resistance

Typical application areas include:

Wire and cable

engineering/industrial accessories

Hose

sheet

textile/fiber

General Information	
Additive	UV stabilizer
Features	Shock absorption
	Noise reduction
	Good UV resistance
	High liquidity
	Ozone resistance
	Good weather resistance
	Heat resistance, high
	Oil resistance
Uses	Handle
	Cable sheath
	Wire sheath
	Washer
	Engineering accessories
	Pipe
	Pipe fittings
	Seals
	Weather-resistant sealing strip
	Sheet
	Fabric
Agency Ratings	EU 2002/96/EC (WEEE)
RoHS Compliance	RoHS compliance

Appearance	Black
Forms	Particle
Processing Method	Blow molding Extrusion Compression molding Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm ³	ASTM D792, ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 1.91mm, molded)	93		ASTM D2240
IRHD Hardness	93		ISO 48
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (1.91mm, molded)	8.48	MPa	ASTM D638, ISO 527-2
Tensile Strength (yield, 1.91mm, molding)	13.1	MPa	ASTM D638, ISO 527-2
Tensile Elongation (fracture, 1.91mm, molded)	300	%	ASTM D638, ISO 527-2
Elastomers	Nominal Value	Unit	Test Method
Tensile Set	24	%	ASTM D412
Tear Strength ¹ (24°C)	62.2	kN/m	ASTM D624
Aging	Nominal Value	Unit	Test Method
Change in Volume			ASTM D471
24°C, 168 hr, in reference fuel B	43	%	ASTM D471
100°C, 168 hr, ASTM Standard Oil (No.1)	-10	%	ASTM D471
100°C, 168 hr, ASTM Standard Oil (No.3)	31	%	ASTM D471

Additional Information

The value listed as Density-Specific Gravity, ASTM D792, was tested in accordance with ASTM D471. Fluid Resistance 7 Days in ASTM Oil no. 1, ISO 1817, at 212 °F: -1% Fluid Resistance 7 Days in IRM 903 Oil no. 3, ISO 1817, at 212 °F: 31% Fluid Resistance 7 Days in ASTM Ref. Fuel no. B, ISO 1817, at 75 °F: 43% Rheological Viscosity, ASTM D3835, 1/300s at 374°F: 820Pa-s

Injection	Nominal Value	Unit
Processing (Melt) Temp	177	°C

NOTE

1. C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

