

# Lumiflon® LF-710F

Fluoropolymer  
Asahi Glass Co., Ltd.

Message:

Applications:  
Architecture  
Coil Coating  
Heavy Duty

General Information		
Uses	Architectural application field	
	Coating application	
Processing Method	Extrusion	
Physical	Nominal Value	Unit
Acid Value	0.00	Mg KOH/g
OH Value	46.0	Mg KOH/g
Thermal	Nominal Value	Unit
Glass Transition Temperature	51.5	°C
Vicat Softening Temperature	90.0	°C
Extrusion instructions		

Heat up temp: 120°C Screw Rotation: 250 rpm Feed rate: 25kg/hour

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT