Softell TKG 259N

Polyolefin

LyondellBasell Industries

Message:

Softell TKG 259N is a UV stabilised, 20 % glassfiber reinforced thermoplastic polyolefin compound for injection moulding. This very low warpage grade has been especially designed for aesthetical automotive interior applications. Softell TKG 259N combines soft touch haptics, a matt surface, a very good sound dampening with a high stiffness and an excellent scratch resistance. The grade is available in colour, pellet form.

| General Information | | | | |
|---|----------------------------------|----------|---------------------|--|
| Filler / Reinforcement | Glass Fiber,20% Filler by Weight | | | |
| Additive | UV Stabilizer | | | |
| Features | Ductile | | | |
| | High Impact Resistance | | | |
| | Low Gloss | | | |
| | Low Shrinkage | | | |
| | Low Warpage | | | |
| | Pleasing Surface Appearance | | | |
| | Scratch Resistant | | | |
| | Soft | | | |
| | Sound Damping | | | |
| | | | | |
| Appearance | Colors Available | | | |
| Forms | Pellets | | | |
| Processing Method | Injection Molding | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Density | 1.05 | g/cm³ | ISO 1183 | |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 7.0 | g/10 min | ISO 1133 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Durometer Hardness | | | ASTM D2240, ISO 868 | |
| Shore D, 3 sec | 56 | | | |
| Shore D, 15 sec | 52 | | | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Stress (Break, 23°C) | 31.0 | MPa | ISO 527-2 | |
| Flexural Modulus (23°C) | 1700 | MPa | ISO 178 | |
| Impact | Nominal Value | Unit | Test Method | |
| Notched Izod Impact Strength | | | ISO 180 | |
| 23°C | 40 | kJ/m² | | |
| 30°C | 10 | kJ/m² | | |
| Thermal | Nominal Value | Unit | Test Method | |

| Heat Deflection Temperature (0.45 MPa, | | | |
|--|-----|----|------------|
| Unannealed) | 100 | °C | ISO 75-2/B |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2