

Epoxies, Ect. 20-2523

Polyurethane
Epoxies, Etc.

Message:

20-2523 is a high performance two component urethane system. This easy to use polyurethane is very low in viscosity and ideal for potting or encapsulating delicate electronic components. 20-2523 exhibits very low shrinkage, stress, and exotherm throughout the cure cycle. This system is also well known for its outstanding thermal shock and excellent dielectric properties.

20-2523 is ideal for potting applications where a wide operating temperature (-55 to +130°C) is required. It is also a good choice when exposure to salt water, mild acids and bases, and aliphatic hydrocarbons is expected.

Features:

- Does not contain MOCA or TDI
- Low stress on components
- Excellent dielectric properties
- Low viscosity
- Easy to handle
- Low shrinkage
- Very good thermal shock and vibration resistance
- Hydrolytic stability

General Information		
Features	Good Thermal Shock Resistance	
	Hydrolytically Stable	
	Low Exotherm	
	Low Shrinkage	
	Low Viscosity	
Uses	Electrical/Electronic Applications	
Appearance	Black	
Processing Method	Encapsulating	
	Potting	
Physical	Nominal Value	Unit
Molding Shrinkage - Flow	0.59	%
Thermal	Nominal Value	Unit
CLTE - Flow	1.6E-4	cm/cm/°C
Electrical	Nominal Value	Unit
Surface Resistivity	1.5E+13	ohms
Thermoset	Nominal Value	Unit
Thermoset Mix Viscosity (25°C)	2950	cP
Additional Information	Nominal Value	Unit
Operating Temperature	-55.0 to 130	°C
Thermal Shock ¹ (-65 to 130°C)	Pass	
Uncured Properties	Nominal Value	Unit
Color	Black	

Mix Ratio by Weight (PBW)		
Part A	100	
Part B	20	
Mix Ratio by Volume (PBV)		
Part A	100	
Part B	23	
Density		
25°C ²	1.23	g/cm ³
25°C ³	1.46	g/cm ³
Viscosity		
25°C ⁴	0.20	Pa · s
25°C ⁵	6.0	Pa · s
Curing Time		
85°C	0.66	hr
65°C	1.5	hr
45°C	2.5	hr
25°C	24	hr
Pot Life ⁶ (25°C)	75	min
Cured Properties	Nominal Value	Unit
Water Absorption		
-- ⁷	0.15	%
-- ⁸	0.44	%
Shore Hardness (Shore D)	50	
Tensile Strength	11.0	MPa
Tensile Elongation at Break	50	%
Electric Strength	25	kV/mm
Relative Permittivity (100 Hz)	4.70	
Volume Resistivity	3.4E+13	ohms · cm
Dissipation Factor (100 Hz)	0.090	
NOTE		
1.	10 cycles	
2.	Part B	
3.	Part A	
4.	Part B	
5.	Part A	
6.	1 lb. mass	
7.	After 24 hours	
8.	After 7 days	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

