

Andur M-11 (97% HQEE/ 3% TMP)

Polyurethane (Polyester, MDI)
Anderson Development Company

Message:

Andur M-11 is an MDI-Ester prepolymer that, when processed with close attention to handling procedures and formulation, produces high quality elastomers. These elastomers perform very well in dynamic applications.

General Information			
Forms	Liquid		
Hardness	Nominal Value	Test Method	
Durometer Hardness		ASTM D2240	
Shaw A	99	ASTM D2240	
Shaw D	60	ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method
Compressive Strength			ASTM D695
2% strain	3.79	MPa	ASTM D695
5% strain	6.89	MPa	ASTM D695
10% strain	10.3	MPa	ASTM D695
15% strain	13.8	MPa	ASTM D695
20% strain	17.2	MPa	ASTM D695
25% strain	22.1	MPa	ASTM D695
50% strain	67.6	MPa	ASTM D695
Taber Abrasion Resistance	47.6	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	22.1	MPa	ASTM D412
200% strain	22.8	MPa	ASTM D412
300% strain	21.7	MPa	ASTM D412
Tensile Strength (Yield)	24.1	MPa	ASTM D412
Tensile Elongation (Break)	350	%	ASTM D412
Compression Set	33	%	ASTM D395
Thermoset	Nominal Value	Unit	
Pot Life	6.0 - 8.0	min	
Demold Time	80	min	
Additional Information			

Die C Tear, ASTM D1004: 900 pliAverage Split Tear, ASTM D1938: 600 pliStoichiometry Curative Level: 90%Parts of curative per 100 parts Andur M-11, 8.9% NCO: 18.76 parts by weightParts of curative per 100 parts Andur M-11, 9% NCO: 18.97 parts by weightParts of curative per 100 parts Andur M-11, 9.1% NCO: 19.18 parts by weightParts of curative per 100 parts Andur M-11, 9.2% NCO: 19.38 parts by weightMix Temperature: Andur M-11: 212°F
Curative HQEE/TMP: 230°F
Stability:
Ambient Temperature, 25°C: 6 Months
Melting Temperature, 60°C: 1 Month
Processing Temperature, 90°C: 12 Hours
Processing Temperature, 105°C: 3 Hours

Injection	Nominal Value	Unit
Mold Temperature	110 - 140	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

