

LNP™ STAT-KON™ MFD02 compound

Polypropylene

SABIC Innovative Plastics

Message:

LNP STAT-KON MFD02 is a compound based on Polypropylene resin containing Glass Fiber, Carbon Powder. Added features of this material include: Electrically Conductive.

Also known as: LNP* STAT-KON* Compound MF-10

Product reorder name: MFD02

General Information			
Filler / Reinforcement	Glass \charcoal powder		
Features	Conductivity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	1.1 - 1.3	%	ASTM D955
Transverse flow: 24 hours	1.1 - 1.3	%	ASTM D955
Vertical flow direction: 24 hours	1.2	%	ISO 294-4
Flow direction: 24 hours	1.2	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2760	MPa	ASTM D638
--	2430	MPa	ISO 527-2/1
Tensile Strength			
Yield	28.3	MPa	ASTM D638
Yield	28.0	MPa	ISO 527-2
Fracture	20.7	MPa	ASTM D638
Fracture	23.0	MPa	ISO 527-2
Tensile Elongation			
Yield	3.2	%	ASTM D638
Yield	2.9	%	ISO 527-2
Fracture	6.1	%	ASTM D638
Fracture	4.2	%	ISO 527-2
Flexural Modulus			
--	2070	MPa	ASTM D790
--	2200	MPa	ISO 178
Flexural Stress	43.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	130	J/m	ASTM D256

23°C ²	15	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	380	J/m	ASTM D4812
23°C ³	28	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	16.7	J	ASTM D3763
--	11.9	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	134	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ⁴	127	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	85.0	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁵	81.0	°C	ISO 75-2/Af
Linear thermal expansion coefficient			
Flow: -40 to 40°C	1.0E-4	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	6.5E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	6.4E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	10 - 1.0E+3	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Rear Temperature	193 - 204	°C	
Middle Temperature	216 - 227	°C	
Front Temperature	238 - 249	°C	
Processing (Melt) Temp	227 - 249	°C	
Mold Temperature	32.2 - 48.9	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

