

KMI PP KM-303IB

Polypropylene Impact Copolymer

KMI Group, Inc.

Message:

KM-303IB is a propylene-ethylene block copolymer designed for film applications. Well designed EP rubber and managing polymerization process to reduce contaminations gives KM-303IB an extremely low fish-eye level

Food Contact Application:

KM-303IB meets the FDA requirements in the Code of Federal Regulations in CFR 177.1520 for food contact.

Characteristics:

Low fish-eye

High Stiffness: Down gauging possibility

High Haze

General Information			
Features	Block Copolymer		
	Rigidity, high		
	Compliance of Food Exposure		
Uses	Films		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Film extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	78		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	28.4	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1370	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Distortion	108	°C	ASTM D648
Optical	Nominal Value	Unit	Test Method
Gloss	10		ASTM D2457
Haze	65	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

