

DURANEX® 300FP

Polybutylene Terephthalate

Polyplastics Co., Ltd.

Message:

Film, Extrusion Molding, High flow, Standard

General Information			
Features	High Flow		
Uses	Film		
Forms	Pellets		
Processing Method	Extrusion		
	Film Extrusion		
Part Marking Code (ISO 11469)	>PBT<		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	70	g/10 min	ISO 1133
Intrinsic Viscosity	0.69		
delta H	51.0	J/g	
Color Number	EF201R		
Thermal	Nominal Value	Unit	
Glass Transition Temperature	35.0	°C	
Melting Temperature	224	°C	
Peak Crystallization Temperature	175	°C	
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT