

NORYL™ SA90 resin

Polyphenylene Ether

SABIC Innovative Plastics

Message:

NORYL SA90 resin is a modified low molecular weight resin with increased hydroxyl functionality. It is designed specifically for use as a reactive component in epoxy and cyanate ester thermosets in electronic, coatings, adhesives, and composites applications. It has outstanding solubility in toluene & methyl ethyl ketone (MEK) and a low solution viscosity. Targeted application areas are in enhancing the performance (e.g. thermal, dielectric, mechanical, flame retardancy, and moisture uptake properties) of epoxy resins used in electronic packaging which include PCB laminates, copper clad laminates, epoxy prepregs, and protective coatings as well as various other composites applications.

General Information			
Features	Low molecular weight		
	Low viscosity		
Uses	Packaging		
	Electrical/Electronic Applications		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm ³	ASTM D792
Hydroxy Equivalent Weight (HEW)	840	g/mol	Internal method
Mn	1600		Internal method
Phenolic End-group Content	2	%	Internal method
Tg (half width)	140	°C	Internal method
Intrinsic Viscosity	0.090	dl/g	Internal method
Solubility			Internal method
Methyl Ethyl Ketone : 21°C	50.0	wt%	Internal method
Toluene : 21°C	50.0	wt%	Internal method
Viscosity			Internal method
50 wt% in methyl ethyl ketone : 25°C	160	mPa·s	Internal method
50 wt% in toluene : 25°C	298	mPa·s	Internal method
Electrical	Nominal Value	Test Method	
Dielectric Constant (1 MHz)	2.54	ASTM D150	
Dissipation Factor (1 MHz)	7.0E-4	ASTM D150	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

